

Coil coated metals — **Test methods**

Part 23: Resistance to humid atmospheres containing sulfur dioxide



BS EN 13523-23:2023 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of EN 13523-23:2026 supersedes BS EN 13523-23:2015, which is withdrawn.

The UK participation in its preparation was entrusted. Technical Committee STI/21, Paint systems and surface preparation for metallic substrates.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This problecation has been prepared in good faith, however no voices intation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2023 Published by BSI Standards Limited 2023

ISBN 978 0 539 22266 1

ICS 17.180.20; 25.220.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 November 2023.

Amendments/corrigenda issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE **EUROPÄISCHE NORM**

EN 13523-23

October 2023

ICS 17.180.20; 25.220.60

English Version

Coil coated metals - Test methods Part 23: Resistance to humid atmospheres de l'accidentaining sulfur dioxide

Tôles prélaquées - Méthodes d'essai - Partie 23.

Bandbeschichtete Metalle - Pr

Résistance à des atmosphères hun dioxyde de s

Bandbeschichtete Metalle - Prüfverfahren - Teil 23: Beständigkeit gegen feuchte, Schwefeldioxid enthaltende Atmosphären

This European Standard was approved by CEN on 12 May 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

COL	ients	e Co.	
Euro	bean foreword 3 duction 5 Scope 6 Normative references 6 Terms and definitions 6 Principle 6 Apparatus 6		
Intro	duction5		
1	Scope6		
2	Normative references		
3	Terms and definitions		
4	Principle		
5	Apparatus6		
6	Sampling/		
7	Test specimens		
8	Procedure		
9	Expression of results		
10	Precision8		
11	Test report8		
Bibli	ography9		

European foreword

This document (EN 13523-23:2023) has been prepared by Technical Committee CEN/TC 139 "P varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either publication of an identical text or by endorsement, at the latest by April 2024, and conflict withdrawn at the latest by April 2024.

Attention is drawn to the possibility that some of the this document may be the subject of patent rights. CEN shall not be held responsible found on fying any or all such patent rights. This document supersedes EN 1352313. N.1.

dition, the following technical modifications have been made:

- the normative references have been updated;
- the text has been editorially revised.

The EN 13523 series, *Coil coated metals* — *Test methods*, consists of the following parts:

- Part 0: General introduction
- Part 1: Film thickness
- Part 2: Gloss
- Part 3: Colour difference and metamerism Instrumental comparison
- Part 4: Pencil hardness
- Part 5: Resistance to rapid deformation (impact test)
- Part 6: Adhesion after indentation (cupping test)
- Part 7: Resistance to cracking on bending (T-bend test)
- Part 8: Resistance to salt spray (fog)
- Part 9: Resistance to water immersion
- Part 10: Resistance to fluorescent UV radiation and water condensation
- Part 11: Resistance to solvents (rubbing test)
- Part 12: Resistance to scratching
- Part 13: Resistance to accelerated ageing by the use of heat
- Part 14: Chalking (Helmen method)
- Part 16: Resistance to abrasion

prEN 13523-23:2022 (E)

- Part 17: Adhesion of strippable films
- Part 18: Resistance to staining

- Part 22: Colour difference Visual comparison

- Part 27: Resistance to humid poultice (Cataplasm test)
- Part 29: Resistance to environmental soiling (Dirt pick-up and striping)

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

Previous work by the European Coil Coating Association (ECCA) has established that this test method is not a reliable or reproducible test for assessing the degree of corrosion on coil coated products but that not a reliable or reproducible test for assessing the degree of corrosion on coil coated products the test method may be used to evaluate the colour fastness of coil coated products. The procedure has been aligned with ISO 22479, except for the amount of sulfationide.

Scope 1

This document describes the procedure for determining the resistance of an organic coating on a metalliq substrate to humid atmospheres containing sulfur dioxide.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document line and are constituted. undated references, the latest edition of the referenced document (intrading any amendments) applies.

EN 13523-0, Coil coated metals - Test methods - Part 0: General introduction

EN 13523-3, Coil coated metals - Test methods Wart 3 comparison 3: Colour difference and metamerism - Instrumental

EN 13523-22, Coil coated metals • Test methods - Part 22: Colour difference - Visual comparison

EN 23270, Paints and varnishes and their raw materials - Temperatures and humidities for conditioning and testing (ISO 3270:1984)

Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at https://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

Principle

Test specimens are exposed to an atmosphere containing sulfur dioxide. The degree of colour change is measured or visually assessed. The degree of other types of degradation, e.g. spotting, streaking, loss of gloss, of the test specimen may also be assessed.

Apparatus 5

An apparatus consisting of an airtight cabinet of capacity (300 ± 10) l, in the base of which is a water-tight trough fitted with a means of heating the water so that it can raise the air temperature in the cabinet to (40 ± 3) °C in about 11/2 h and maintain this temperature for a total period of 8 h from the commencement of the test cycle.

The dimensions and design of the cabinet are not critical provided the stand for supporting the test panels is made of, or coated with an inert material and is of sufficient size to accommodate test specimens with a total surface area of (0.5 ± 0.1) m².

The cabinet shall also be constructed of an inert material and have a roof which prevents condensed moisture dripping onto the test specimens.

The cabinet shall be provided with a means of relieving excess pressure and a gas inlet pipe which shall be situated immediately above the water trough.

A gas cylinder or gas generating apparatus fitted with appropriate regulating and measuring apparatus to ensure the supply of the correct volume of sulfur dioxide.

The cabinet shall also be provided with a means of controlling the temperature which shall be measured in the space above the test specimens.

The reverse face and edges of the panel shall be coated with a suitable protective material such as a

See EN 13523-0.

The test specimens shall be nominally 150 mm, unless otherwise specified or agreed.

The reverse face and edges of the panel shall be coated with a suitable protective material lacquer or adhesive tape the five at attack by the sulfur dioxide.

3 Procedure

Ondition the test specimens for at least 24^{-1} equired, for instance in case of 2^{-1} midity of $(50 \pm 5)^{-0.6}$ Condition the test specimens for at least 24 h under ambient conditions of temperature and humidity. If required, for instance in case of dispute, conditioning shall be carried out at (23 ± 2) °C and a relative

During this conditioning, the test specimens shall not be exposed to direct sunlight.

After conditioning, carry out the test procedure as soon as possible.

Set-up the testing apparatus (Clause 5) in an environment protected from draughts and direct sunlight.

Arrange the test specimens vertically in the test apparatus so that they are at least 100 mm from any wall or cover, at least 20 mm from each other and so that the lower edges of the specimens are at least 200 mm above the water. Where possible, arrange the test specimens at the same level for comparative tests. Care shall be taken to ensure that water condensed on upper specimens does not drip onto the lower specimens.

As the same volume of sulfur dioxide is introduced at each test cycle, the total surface area of the test specimens in the cabinet is important. For comparative tests, the total test specimen area in the cabinet should be the same.

Fill the trough with (2.0 ± 0.2) l of distilled or deionised water. Prior to each test cycle, drain and renew this distilled or deionised water.

After closing the apparatus, introduce (2.0 ± 0.2) l of sulfur dioxide into the test cabinet, switch on the heating appliance and raise the air temperature to (40 ± 3) °C in about 1 1/2 h. Maintain this temperature for a total period of 8 h from the commencement of the test cycle. At the end of this period, switch off the heating appliance and ensure the chamber is fully purged. Open the door completely or raise the hood of the apparatus to at least the height of the upper edges of the test specimens.

Leave the test specimens in the cabinet for a further 16 h. This constitutes one test cycle. Start a new cycle by changing the water and introducing fresh sulfur dioxide. Repeat for a total of 5 test cycles. Cycles shall be continuous and without interruption.

At the end of 5 test cycles, remove the test specimens from the cabinet, wash with clean water, blot with absorbent paper and immediately examine the whole test surface of each specimen for colour change using EN 13523-3 or EN 13523-22.

Measure or assess visually the degree of colour change. The degree of other types of degradation, e.g. spotting, streaking, loss of gloss, of the test specimen may also be assessed.

prEN 13523-23:2022 (E)

Expression of results

If specified, report observations on spotting, streaking, loss of gloss and any other degradation effects.

10 Precision

No precision data are currently available.

11 Test report

The test report shall contain at least the following into mation:

a) all details necessary to identify the product tested; Express the result as the mean of the measurements taken or the visual difference in colour.

- a reference to this document i.e. EN 13523-23:2023;
- the results of the test, as indicated in Clause 9;
- any deviation from the test method specified;
- any unusual features (anomalies) observed during the test;
- the date of the test. f)

8

Bibliography

- EN 1396, Aluminium and aluminium alloys Coil coated sheet and strip for general applications Specifications

 EN 10169, Continuously organic coated (coil coated) steel flat profess Technical delivery conditions

 ISO 22479:2019, Corrosion of metals and alloys Collfur dioxide test in a humid atmosphere (fixed gas method) [1]
- [2]
- [3]

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, standards and others to shape their combined experience and experience

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup. com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced in any format to create an additional copy. This includes scanning of the document

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.

With British Standards Online (BSOL) you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a BSI Subscribing Member.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop

With a Multi-User Network Licence (MUNL) you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001 Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

