



BSI Standards Publication

<http://www.china-gauges.com/>

**Buildings and civil engineering works - Sealants -
Determination of change in mass and volume (ISO
10563:2017)**

National foreword

This British Standard is the UK implementation of EN ISO 10563:2017. It is identical to ISO 10563:2017. It supersedes BS EN ISO 10563:2005, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/547, Sealants for building and construction.

A list of organizations representing this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017
Published by BSI Standards Limited 2017

ISBN 978 0 580 90985 6

ICS 91.100.50

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 September 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN ISO 10563

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2017

ICS 91.100.50

Supersedes EN ISO 10563:2005

English Version

Buildings and civil engineering works - Sealants -
Determination of change in mass and volume (ISO
10563:2017)

Bâtiments et ouvrages de génie civil - Mastics -
Détermination des variations de masse et de volume
(ISO 10563:2017)

Hochbau - Fugendichtstoffe - Bestimmung der
Änderung von Masse und Volumen (ISO 10563:2017)

This European Standard was approved by CEN on 22 April 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

European foreword

This document (EN ISO 10563:2017) has been prepared by Technical Committee ISO/TC 59 "Buildings and civil engineering works".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2017 and conflicting national standards shall be withdrawn at the latest by December 2017.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 10563:2005.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 10563:2017 has been approved by CEN as EN ISO 10563:2017 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus and materials	1
6 Preparation of test specimens	2
6.1 For non-sagging sealant.....	2
6.2 For self-levelling sealant.....	2
7 Test procedure	3
7.1 General.....	3
7.2 Preconditioning.....	3
7.3 Specific conditioning.....	3
8 Calculation and expression of results	3
8.1 Change in mass.....	3
8.2 Change in volume.....	4
9 Test report	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 59, *Buildings and civil engineering works*, Subcommittee SC 8, *Sealants*.

This third edition cancels and replaces the second edition (ISO 10563:2005), which has been technically revised.

The main changes compared to the previous edition are as follows:

- To include the determination of loss of volume for self-levelling sealants;
- To precise the target of the test: not intended to determine the absolute maximum value of loss of volume of a tested sealant, but it is an indicative measurement of the loss of volume under specified parameters;
- To precise the conditioning time: (28 days +/- 3 hours) at (23 +/- 2) °C & (50 +/- 10)% RH, then (7 days +/- 2 hours) at (70 +/- 2) °C;
- To precise the apparatus;
- To precise the localization of the filled rings in the oven.

Buildings and civil engineering works — Sealants — Determination of change in mass and volume

1 Scope

This document specifies a method for the determination of the change of mass and the change of volume of self-levelling and non-sagging sealants used in joints in building construction.

NOTE This test procedure is not intended to determine the absolute maximum value of loss of volume of a tested sealant, but it is an indicative measurement of the loss of volume under specified parameters.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6927, *Buildings and civil engineering works — Sealants — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6927 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

Test specimens consist of either metal rings filled with non-sagging sealant or metal moulds filled with self-levelling sealant. The rings or moulds are weighed in air and in water, before and after filling, before and after specific conditioning. The change in mass and in volume of the tested sealant is calculated.

5 Apparatus and materials

5.1 Rings of non-corrosive metal for non-sagging sealant, having the following dimensions: inner diameter, (30 ± 1) mm; height, $(10 \pm 0,1)$ mm. A hook or loop is fixed to each ring to suspend it from a string for the weighing procedure.

5.2 Anti-adherent substrate for non-sagging sealant, for the preparation of test specimens.

EXAMPLE Wet paper.

5.3 Moulds of non-corrosive metal for self-levelling sealant, having the following dimensions: inner diameter, (30 ± 1) mm; inner depth, $(10 \pm 0,1)$ mm.

5.4 Balance, with an accuracy of 0,01 g, capable of being used to weigh the test specimens in air and immersed in test liquid.

5.5 Test liquid, at a temperature of (23 ± 2) °C, consisting of water with the addition of up to 0,25 % (by mass) of a low-foam surfactant. In the case of water-sensitive sealants, laboratory grade 2,2,4-trimethylpentane (iso-octane) shall be used.

5.6 Preconditioning chamber, capable of being controlled at (23 ± 2) °C and (50 ± 10) % relative humidity.

5.7 Ventilated oven, with a volume of (200 ± 100) L, capable of being controlled at (70 ± 2) °C.

5.8 Container, for the immersion of the test specimens in the test liquid.

6 Preparation of test specimens

6.1 For non-sagging sealant

The sealant and the metal rings (5.1) shall be brought to (23 ± 2) °C. Three test specimens shall be prepared for each property to be tested.

Each metal ring shall be weighed in air (mass m_1) using the balance (5.4), and, for the volume test, also in the test liquid (5.5) (mass m_2).

The rings shall be set on the anti-adherent substrate (5.2) and filled with the sealant to be tested using the following procedure.

- a) The formation of air bubbles shall be avoided.
- b) The sealant shall be pressed on the inner surfaces of the metal rings to ensure intimate contact.
- c) The sealant surface shall be tooled so that it is flush with the upper rim of the metal rings.
- d) The test specimens shall be removed immediately from the anti-adherent substrate such that the reverse side of the sealant is flush.
- e) The filled rings shall be weighed immediately in air (mass m_3), and, for the volume change, also in the test liquid (mass m_4). For water-borne sealants, these measurements shall be carried out after 60 min and shall be completed within 30 s.

6.2 For self-levelling sealant

The sealant and the metal moulds (5.3) shall be brought to (23 ± 2) °C. Three test specimens shall be prepared for each property to be tested.

Each metal mould shall be weighed in air (mass m_1) using the balance (5.4), and, for the volume test, also in the test liquid (5.5) (mass m_2).

The moulds shall be filled with the sealant to be tested using the following procedure.

- a) The formation of air bubbles shall be avoided.
- b) The sealant shall be pressed on the inner surfaces of the metal moulds to ensure intimate contact.
- c) The sealant surface shall be tooled so that it is flush with the upper rim of the metal moulds.
- d) The filled moulds shall be weighed immediately in air (mass m_3), and, for the volume change, also in the test liquid (mass m_4). For water-borne sealants, these measurements shall be carried out after 60 min and shall be completed within 30 s.

7 Test procedure

7.1 General

During the test procedure, the test specimens shall be positioned:

- either vertically for non-sagging sealant, or
- horizontally for self-levelling sealant.

7.2 Preconditioning

The test specimens shall be conditioned in the chamber (5.6) at (23 ± 2) °C and (50 ± 10) % relative humidity, during $28 \text{ d} \pm 3 \text{ h}$.

7.3 Specific conditioning

After preconditioning according to 7.2, the test specimens are placed in the ventilated oven (5.7), using the following procedure.

- a) In case of several tested sealants, only the same chemical family sealants shall be placed in the oven in the same conditioning time.
- b) All test specimens shall be placed in the same shelf at mid height, in the oven.
- c) All test specimens shall be placed at a minimum distance of 8 cm from the internal wall of the oven.
- d) Each test specimen shall be placed at a minimum distance of 8 cm from another test specimen.

Condition the test specimens in the ventilated oven regulated at (70 ± 2) °C, during $7 \text{ d} \pm 2 \text{ h}$. The door of the oven shall be maintained in a closed position during the specific conditioning.

After the specific conditioning in the oven, the test specimens shall be stored in the chamber (5.6) at (23 ± 2) °C and (50 ± 10) % relative humidity, during (24 ± 2) h.

The test specimens shall be weighed immediately in air (mass m_5) and, for the volume change, also in the test liquid (mass m_6).

8 Calculation and expression of results

8.1 Change in mass

For each test specimen, the change in mass, Δm , expressed as a percentage, shall be calculated using [Formula \(1\)](#), rounded to the nearest 0,1 %:

$$\Delta m = \frac{m_5 - m_3}{m_3 - m_1} \times 100 \quad (1)$$

where

- m_1 is the mass, expressed in grams, of the metal ring or metal mould before filling with the sealant, measured in air (see [Clause 6](#));
- m_3 is the mass, expressed in grams, of the test specimen immediately after preparation, measured in air (see [Clause 6](#));
- m_5 is the mass, expressed in grams, of the test specimen immediately after conditioning, measured in air (see [7.3](#)).

The arithmetic mean of the change in mass of the three specimens shall be taken as the test result, rounded to the nearest 0,1 %.

8.2 Change in volume

For each test specimen, the change in volume, ΔV , expressed as a percentage, shall be calculated using [Formula \(2\)](#), rounded to the nearest 0,1 %:

$$\Delta V = \frac{(m_5 - m_6) - (m_3 - m_4)}{(m_3 - m_4) - (m_1 - m_2)} \times 100 \quad (2)$$

where

- m_2 is the mass, expressed in grams, of the metal ring before filling with the sealant, measured in the test liquid (see [Clause 6](#));
- m_4 is the mass, expressed in grams, of the test specimen immediately after preparation, measured in the test liquid (see [Clause 6](#));
- m_6 is the mass, expressed in grams, immediately after conditioning, measured in the test liquid (see [7.3](#));
- m_1, m_3, m_5 are defined in [8.1](#).

The arithmetic mean of the change in volume of the three specimens shall be taken as the test result, rounded to the nearest 0,1 %.

9 Test report

The test report shall include the following information:

- a) the test laboratory's name and date of test;
- b) a reference to this document, i.e. ISO 10563;
- c) the name, type (chemical family) and colour of sealant;
- d) the batch of sealant from which the test specimens were produced;
- e) the parameters of the ventilated oven (mechanically or naturally ventilated; air exchange rate, if known) and its flap position (open or closed);
- f) the individual values of the change in mass and/or volume for each test specimen;
- g) the arithmetic means of the change in mass and/or the change in volume for the tested sealant;
- h) any deviations from the specified test conditions.

<http://www.china-gauges.com/>

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK